



ARASH MAHYA PARAFFIN MANUFACTURING CO.

SEMI-REFINED PARAFFIN WAX

PRODUCT DATA SHEET

CHARACTERISTIC	RESULT	METHOD
Oil Content	2-4 %wt	ASTM D-721
Melting Point	62 – 66 ° C	ASTM D-87
Flash Point	220-240 ° C	ASTM D-92
Kinematic Viscosity at 100 ° C	6-7.5 CST	ASTM D-445
Colour (Lovibond)	White	Method (2"cell)

Packing:

Carton / PP Bags / Metalized Bags

Application:

Candles, Match sticks, Tires, cosmetics, wooden boards, tarpaulin, etc.

Head Office:

No 48, 9th Flr, Mina Tower,
Sadeqieh Square,
Tehran, Iran.

Tel:

+98 21 440 710 24
+98 21 440 710 26
+98 21 440 710 28

Email:

info@arashmahya.com
arashmahyaco@gmail.com

Website: www.arashmahya.com