



# ARASH MAHYA PARAFFIN MANUFACTURING CO.

## RESIDUE WAX

### PRODUCT DATA SHEET

CHARACTERISTIC	RESULT	METHOD
Oil Content	30-40 %wt	ASTM D-721
Drop Melting Point	40-50°C	ASTM D-127
Flash Point	230 – 250°C	ASTM D-92
Kinematic Viscosity at 100 °C	6-7.5 CST	ASTM D-445
Penetration at 25°C	100-150 (1/10 mm)	ASTM D-937
Colour (Lovibond)	Yellowish Brown	Method (2"cell)

**Packing:** Drums

**Application:**

Tire, Rubber, Plastic, Match stick, Polish, etc.

**Head Office:**

No 48, 9<sup>th</sup> Flr, Mina Tower,  
Sadeqieh Square,  
Tehran, Iran.

**Tel:**

+98 21 440 710 24  
+98 21 440 710 26  
+98 21 440 710 28

**Email:**

info@arashmahya.com  
arashmahyaco@gmail.com

**Website:** [www.arashmahya.com](http://www.arashmahya.com)