



# ARASH MAHYA PARAFFIN MANUFACTURING CO.

## HEAVY SLACK WAX

### PRODUCT DATA SHEET

CHARACTERISTIC	RESULT	METHOD
Oil Content	12% wt	ASTM D-721
Melting Point	54 – 62 ° C	ASTM D-938
Flash Point	Min. 245 ° C	ASTM D-92
Density at 15 ° C	0.885 kg/L	ASTM D-4052
Colour (Lovibond)	Brown	Method (2"cell)

#### Packing:

Drum / Metalized Bag

#### Application:

Paraffin manufacturing, fuel industries, etc.

#### Head Office:

No 48, 9<sup>th</sup> Flr, Mina Tower,  
Sadeqieh Square,  
Tehran, Iran.

#### Tel:

+98 21 440 710 24  
+98 21 440 710 26  
+98 21 440 710 28

#### Email:

info@arashmahya.com  
arashmahyaco@gmail.com

**Website:** [www.arashmahya.com](http://www.arashmahya.com)